



# PERLA



OFFICE  
PERLA Tegular

PERLA is a fully C2C Bronze certified range with a smooth laminated finish providing balanced acoustic performance combining both sound absorption and sound attenuation.



















### Key features

- Winning balance of sound attenuation and absorption
- Enhanced product durability
- High level of light reflectance: 86%
- Better finish and more durable edges
- C2C Bronze certified / ISO 5 / A+
- Available with SL2 MicroLook 90 edge detail

### Application areas

Ideal for working and learning applications....



EDGE DETAIL	BOARD	TEGULAR	MICROLOOK 90								
<b>THICKNESS (mm)</b>	<b>17</b>	<b>17</b>	<b>17</b>								
<b>MODULES (mm)</b>	600 x 600 ..... 2801M 625 x 625 ..... 2801D 1200 x 600 ..... 2802M	600 x 600 ..... 2803M	600 x 600 ..... 2805M 625 x 625 ..... 2805D 1200 x 600 ..... 5180M 1500 x 600 ..... 5181M								
<b>SUSPENSION SYSTEMS</b>	Prelude 24 XL <sup>2</sup> / TL <sup>2</sup> Prelude 24 Sixty <sup>2</sup> XL <sup>2</sup> / TL <sup>2</sup>	Prelude 24 XL <sup>2</sup> / TL <sup>2</sup> Prelude 24 Sixty <sup>2</sup> XL <sup>2</sup> / TL <sup>2</sup>	Prelude 15 TL / XL <sup>2</sup> Interlude HRC XL <sup>2</sup> Silhouette 6mm XL <sup>2</sup>								
<b>COLOURS</b>	 Global White										
<b>SUSTAINABILITY</b>	    										
	<sup>1</sup> Depends on thickness, edge detail and size of tile.										
<b>ACOUSTICS</b>				<b>Hz α<sub>p</sub></b>							
	<b>D<sub>nfw</sub></b>	<b>R<sub>w</sub></b>	<b>α<sub>w</sub></b>	Class	NRC	125	250	500	1000	2000	4000
Board, Tegular, MicroLook 90	<b>35 dB</b>	<b>18 dB</b>	<b>0.65(H)</b>	C	0.70	0.35	0.40	0.60	0.85	0.95	1.00
<b>FIRE REACTION</b>		EEA Euroclass A2-s1, d0 EN 13501-1	RUS KM1 (G1, V1, D1, T1) FZ 123								
<b>OTHER PERFORMANCES &amp; FEATURES</b>	 86%	 95% RH	 ISO 5 ISO 14644-1								
	 λ = 0.052 W/m K EN 12667 & ISO 8301	 4.6 kg/m <sup>2</sup>									
											
<b>CUSTOM OPTIONS</b>	 Dimensions										